

**PRODUCT DESCRIPTION**

An Epoxy-Polyester Hybrid powder coating designed for good electrostatic properties and surface flow over a wide range of film thickness.

**APPEARANCE**

**Color:** Gray  
**Gloss:** Semi-Gloss  
**Finish:** Smooth

If the significant surface is too small or unsuitable for the gloss to be measured with the gloss meter, the gloss should be compared visually with the reference sample

**PROPERTIES**

Property	Result
Specific Gravity (S.G.)	1.71 +/- 0.05
Theoretical Coverage at 1 mil (25.4 µm)	113 ft <sup>2</sup> /lb (23.1 m <sup>2</sup> /kg)

The technical data provided below are typical for this product when applied as follows:

**Substrate:** Cold Rolled Steel  
**Film thickness:** 2.0-3.0 mils (51 - 76 µm)

Typical values when tested.

Property	Standard	Result
Gloss @ 60°	ASTM D523-14	58-68
Adhesion	ASTM D3359	5B
Impact Resistance	ASTM D2794-90	80 in-lbs
Reverse Impact Resistance	ASTM D2794-90	80 in-lbs
Pencil Hardness	ASTM D3363	H
Surface Resistance		10 <sup>4</sup> – 10 <sup>9</sup> ohms

**APPLICATION****Pre-cleaning:**

Clean all surfaces to be coated in accordance with SSPC-SP-1, Solvent Cleaning prior to additional surface preparation or coating application. Surface must be clean, dry and free of any dirt, dust, oil, and all other visible contaminants that could potentially interfere with adhesion of the coating.

**Surface preparation:**

The overall performance of the coating system is largely dependent on the nature of the substrate and the type and quality of the surface preparation. Surfaces to receive coating may be prepared using liquid pretreatment designed for high temperature service. For optimal results, we recommend abrasive blast cleaning in accordance with SSPC SP-10/NACE #2, ISO SA 2.5, anchor profile 0.75 to 1.5 mils (19 to 38 microns). Before using phosphate pretreatments, contact your supplier for temperature limitations. Substrates also have structural physical temperature limits that must be observed.

**Powder Application Conditions**

Cure Schedule *	Temperature	Time
	400 °F (204 °C)	10 minutes

Film Build	Minimum Thickness	Maximum Thickness
	2.0 mils (51 µm)	3.0 mils (76 µm)

\*Other curing schedules may be used upon technical approval. Cure schedule is based on substrate temperature.

**Equipment**

Electrostatic application to room temperature substrate is recommended. Suitable for Corona charging equipment, reduced voltages can improve coating film thickness uniformity. This product may be applied to warm substrate for increased film thickness.

**STORAGE**

Keep in a dry cool area. Maximum temperature of 77°F (25 °C) and maximum relative humidity 60%. If stored longer than 12 months a quality test is recommended.

**CAUTION :** Adequate health and safety precautions should be observed during storage, handling, use and curing periods.

**READ MATERIAL SAFETY DATA SHEETS BEFORE USING THIS PRODUCT**

**DISCLAIMER**

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use under then existing conditions. Our liability for breach of warranty, strict liability in tort, negligence or otherwise is limited exclusively to replacement of the product or refund of its price. Under no circumstances are we liable for incidental or consequential damages.